



Technical Sheet

Feldspar / Feldespato VGL325

XRF Chemical Analysis Análisis químicos XRF

Oxides / Oxidos	%
SiO ₂	68.3
Al ₂ O ₃	18.40
Fe ₂ O ₃	0.29
TiO ₂	0.06
CaO	0.42
MgO	<0.05
K ₂ O	5.63
Na ₂ O	6.64
L.o.I.	0.30

Mineralogy / Mineralogía

	%
Na-K Feldspar / Na-K Feldespato	81
Quartz / Cuarzo	18
Others / Otros	1

Grainsize Distribution Distribución Granulométrica

Fraction / Fracción	63 µm
Retained on 63 µm sieve Retenido en tamiz de 63 µm	<1.0 %

Other Characteristics Otras Características

Moisture / Humedad	0.1 % max
Hardness / Dureza (mohs)	6
pH	6.5 - 7

Product Description:

Ventilated Na-K feldspar for ceramic applications (also in glaze). Available packages: 1000 Kg big-bags and bulk. Production site: Tlaxcala plant

Descripción Producto:

Na-K Feldespato ventilado para producción de cerámicos (esmalte). Disponible en Jumbo bags de 1000 Kg y Bulk. Sitio de producción : planta de Tlaxcala

