



Technical Sheet

Feldspar / Feldespato F1MSR

XRF Chemical Analysis Análisis químicos XRF

Oxides / Oxidos	%
SiO ₂	68.2
Al ₂ O ₃	18.00
Fe ₂ O ₃	0.32
TiO ₂	0.10
CaO	0.40
MgO	<0.05
K ₂ O	5.88
Na ₂ O	6.71
L.o.I.	0.30

Mineralogy / Mineralogía	%
Na-K Feldspar / Na-K Feldespato	78
Quartz / Cuarzo	21
Others / Otros	1

Grainsize Distribution Distribución Granulométrica

Fraction / Fracción	<2000 μ m
Retained on 106 μ m sieve	70.0 %
Retenido en tamiz de 106 μ m	

Other Characteristics Otras Características

Moisture / Humedad	0.1 % max
Hardness / Dureza (Mohs)	6
pH	6.5 - 7

Product Description:

Milled Na-K feldspar for glass applications.
Available packages: big-bags and bulk.
Production site: Tlaxcala plant

Descripción Producto:

Na-K Feldespato molido para producción de vidrio.
Disponibile en jumbo bags de 1000 Kg y
bulk. Sitio de producción: Planta de Tlaxcala



Forwarding Address c/o: Dirección en Italia:

MINERALI INDUSTRIALI S.r.l.
Piazza Martiri della Libertà n. 4; 28100, NOVARA (ITALY)
Tel. 0039/0321/39025 - Fax: 0039/0321/391 e-mail: info@min-ind.it

